



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Correlating Densification and Crack Resistance in Sodium Aluminoborate Glasses

Januchta, Kacper; Youngman, Randall E.; Goel, Ashutosh; Bauchy, Mathieu; Rzoska, Sylwester J.; Bockowski, Michal; Smedskjær, Morten Mattrup

Publication date:
2017

Document Version
Early version, also known as pre-print

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Januchta, K., Youngman, R. E., Goel, A., Bauchy, M., Rzoska, S. J., Bockowski, M., & Smedskjær, M. M. (2017). *Correlating Densification and Crack Resistance in Sodium Aluminoborate Glasses*. Abstract from 7th International Workshop on Flow and Fracture of Advanced Glasses, Aalborg, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Correlating Densification and Crack Resistance in Sodium Aluminoborate Glasses

Kacper Januchta¹, Randall E. Youngman², Ashutosh Goel³, Mathieu Bauchy⁴, Sylwester J. Rzoska⁵, Michal

Bockowski⁵, Morten M. Smedskjaer¹

¹ *Department of Chemistry and Bioscience, Aalborg University, Aalborg, Denmark*

² *Science and Technology Division, Corning Incorporated, Corning, USA*

³ *Department of Materials Science and Engineering, Rutgers, The State University of New Jersey, USA*

⁴ *Department of Civil and Environmental Engineering, University of California, Los Angeles, USA*

⁵ *Institute of High-Pressure Physics, Polish Academy of Sciences, Warsaw, Poland*

Sodium aluminoborate glasses exhibit a high resistance to indentation cracking compared to most oxide glasses. In this work, we study seven compositions with varying Al₂O₃ and B₂O₃ contents, but fixed Na₂O content. Vickers indentation analysis shows that the nature of the network-former is decisive for the crack resistance, with Al₂O₃-rich compositions exhibiting the highest crack resistance values in excess of 20 N. The origin of such high crack resistance is investigated by probing the response of the studied glasses to compaction in terms of their network structure and their macroscopic mechanical properties. ¹¹B MAS NMR analysis indicates that the glasses with the lower fraction of tetrahedral boron (i.e., where Na-ions are primarily associated with tetrahedral Al-units) are more prone to change their short-range order upon 1 GPa compression treatment carried out at T_g . The extent of pressure-induced structural changes is in good agreement with the extent of the accompanying increases in density, hardness, and indentation modulus. We conclude that the high crack resistance originates from the glasses' high potential to rearrange their structure when subjected to pressure. Interestingly, we observe that the volume recovery ratio (i.e., the extent of load-induced densification) exhibits a local maximum around the metaluminous composition, which does not support the observed linear compositional scaling in crack resistance. This disagreement is discussed in terms of the structural changes occurring due to the abrupt change in chemistry, and held against the positive correlation between crack resistance and compression-induced extent of densification.