

## Assessment of the Reliability of Concrete Slab Bridges

Thoft-Christensen, Palle; Jensen, F. M.; Middleton, C. R.; Blackmore, A.

*Publication date:*  
1996

*Document Version*  
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

*Citation for published version (APA):*  
Thoft-Christensen, P., Jensen, F. M., Middleton, C. R., & Blackmore, A. (1996). *Assessment of the Reliability of Concrete Slab Bridges*. Dept. of Building Technology and Structural Engineering. Structural Reliability Theory Vol. R9616 No. 157

### General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

### Take down policy

If you believe that this document breaches copyright please contact us at [vbn@aub.aau.dk](mailto:vbn@aub.aau.dk) providing details, and we will remove access to the work immediately and investigate your claim.



---

# INSTITUTTET FOR BYGNINGSTEKNIK

DEPT. OF BUILDING TECHNOLOGY AND STRUCTURAL ENGINEERING  
AALBORG UNIVERSITET • AUC • AALBORG • DANMARK

---

## STRUCTURAL RELIABILITY THEORY PAPER NO. 157

Presented at the 7th IFIP WG7.5 Working Conference on Reliability and Optimization of Structural Systems, Boulder, Colorado, USA, April 2-4, 1996

---

P. THOFT-CHRISTENSEN, F. M. JENSEN, C. R. MIDDLETON & A. BLACKMORE  
ASSESSMENT OF THE RELIABILITY OF CONCRETE SLAB BRIDGES  
MAY 1996

---

ISSN 1395-7953 R9616



The STRUCTURAL RELIABILITY THEORY papers are issued for early dissemination of research results from the Structural Reliability Group at the Department of Building Technology and Structural Engineering, University of Aalborg. These papers are generally submitted to scientific meetings, conferences or journals and should therefore not be widely distributed. Whenever possible reference should be given to the final publications (proceedings, journals, etc.) and not to the Structural Reliability Theory papers.

**STRUCTURAL RELIABILITY THEORY**  
**PAPER NO. 157**

Presented at the 7th IFIP WG7.5 Working Conference on Reliability and Optimization of Structural Systems, Boulder, Colorado, USA, April 2-4, 1996

---

**P. THOFT-CHRISTENSEN, F. M. JENSEN, C. R. MIDDLETON & A. BLACKMORE**  
**ASSESSMENT OF THE RELIABILITY OF CONCRETE SLAB BRIDGES**  
**MAY 1996** **ISSN 1395-7953 R9616**

---





## ASSESSMENT OF THE RELIABILITY OF CONCRETE SLAB BRIDGES

P.Thoft-Christensen\*, F.M.Jensen\*\*, C.R.Middleton\*\*\* & A.Blackmore\*\*\*

\*Aalborg University, Aalborg, Denmark, \*\*CSRconsult, Aalborg, Denmark,

\*\*\*Cambridge University, Cambridge, UK

### 1. Introduction

This paper is based on research performed for the Highways Agency, London, UK under the project DPU/9/44 *"Revision of Bridge Assessment Rules Based on Whole Life Performance: Concrete Bridges"*. It contains details of a methodology which can be used to generate Whole Life (WL) reliability profiles.

### 2. Limit States

Two limit states are selected for the reliability analysis:

- an ultimate limit state (ULS): collapse limit state (using yield line analysis)
- a serviceability limit state (SLS): crack width limit state (using linear elastic analysis)

#### 2.1 Collapse (yield line) limit state

The following safety margin is used

$$Z = VE_D - W_D \quad (1)$$

where  $V$  is a model uncertainty variable,  $E_D$  is the energy dissipated in yield lines, and  $W_D$  is the work done by the applied loads.

The plastic collapse analysis and estimation of the load are performed using the COBRAS program, see [1]. The reliability analysis (element and system) is done using programs RELIAB01 and RELIAB02, see [2,3]. The RELIAB and COBRAS programs have been interfaced and include an optimisation algorithm to determine the optimal yield line pattern for each iteration of the reliability analysis. In [4] it is shown that using a fixed deterministic yield line pattern in the reliability analysis may lead to erroneous results. The estimation of the deterioration of the steel reinforcement is based on the program CORROSION, see [5].

The basic variables used in the yield line ULS are: thickness of slab, cube strength of concrete, density of concrete, depth of reinforcement, yield strength of reinforcement, and two load parameters.

## 2.2 Crack width limit state

Cracking shall be limited to a level that will not impair the proper functioning of the structure or cause its appearance to be unacceptable. In the absence of specific requirements (e.g. water tightness), it may be assumed that limitation of the maximum design crack width to about 0.3 will generally be satisfactory for reinforced concrete members with respect to appearance and durability.

The design crack width may be obtained from (see [6])

$$w_k = \beta s_{rm} \varepsilon_{sm} \quad (2)$$

where  $w_k$  is the design crack width,  $s_{rm}$  is the average final spacing,  $\varepsilon_{sm}$  is the mean strain allowing, under the relevant combination of loads, for the effects of tension stiffening, shrinkage, etc., and  $\beta$  is a coefficient relating the average crack width to the design value. For load induced cracking  $\beta = 1.7$ . The value of  $\varepsilon_{sm}$  may be calculated from the relation

$$\varepsilon_{sm} = \frac{\sigma_s}{E_s} (1 - \beta_1 \beta_2 (\frac{\sigma_{sr}}{\sigma_s})^2) \quad (3)$$

where  $\sigma_s$  is the stress in the reinforcement calculated on the basis of a cracked section,  $\sigma_{sr}$  is the stress in the reinforcement calculated on the basis of a cracked section under the loading conditions causing first cracking.

$\beta_1$  is a coefficient which takes account of the bond properties of the bars. It is = 1.0 for high bond bars, and = 0.5 for plain bars.  $\beta_2$  is a coefficient which takes account of the duration of the loading or of repeated loading. It is = 1.0 for single, short term loading, and = 1.5 for a sustained load or for many cycles of repeated loading.

The average final crack spacing (in mm) for members subjected dominantly to flexure or tension can be calculated from the equation

$$s_{rm} = 50 + 0.25 k_1 k_2 \phi / \rho_r \quad (4)$$

where  $\phi$  is the bar size in use (or the average bar size).  $\rho_r$  is the effective reinforcement ratio,  $A_s / A_{c,eff}$ , where  $A_s$  is the area of reinforcement contained within the effective tension area,  $A_{c,eff}$ .  $k_1$  is a coefficient which takes account of the bond properties of the bar. It is = 0.8 for high bond bars and = 1.6 for plain bond bars.  $k_2$  is a coefficient which takes account of the strain distribution. It is = 0.5 for bending and = 1.0 for pure tension.

The crack width limit state can then be formulated by

$$g(\cdot) = w_{max} - z_c w_k \quad (5)$$

where  $z_c$  is a model uncertainty stochastic variable.

The stochastic variables used in the crack SLS are: concrete cover, distance between reinforcement bars, diameter of reinforcement bars, thickness of slab, elastic modulus of reinforcement bars, tensile strength of concrete, external bending moment, and one model uncertainty variable.

### 3. Deterioration modelling

Several models can be used to model the deterioration of reinforcement steel in concrete slabs. However, there is a general agreement that the model presented below is acceptable in most cases.

Corrosion initiation period refers to the time during which the passivation of steel is destroyed and the reinforcement starts to corrode actively. Practical experience of bridges in wetter countries like UK shows that chloride ingress is far bigger a problem than carbonation.

The rate of chloride penetration into concrete, as a function of depth from the concrete surface and time, can be represented by Fick's law of diffusion as follows:

$$\frac{\delta c}{\delta t} = D_c \frac{\delta^2 c}{\delta x^2} \quad (6)$$

where  $c$  is the chloride ion concentration, as % of the weight of cement, at distance  $x$  cm from the concrete surface after  $t$  seconds of exposure to the chloride source.  $D_c$  is the chloride diffusion coefficient expressed in  $\text{cm}^2/\text{sec}$ . The solution of the differential equation (6) is

$$C(x, t) = C_0 \left\{ 1 - \operatorname{erf} \left( \frac{x}{2\sqrt{D_c \cdot t}} \right) \right\} \quad (7)$$

where  $C_0$  is the equilibrium chloride concentration on the concrete surface, as % of the weight of cement,  $x$  is the distance from the concrete surface in cm,  $t$  is the time in sec,  $\operatorname{erf}$  is the error function,  $D_c$  is the diffusion coefficient in  $\text{cm}^2/\text{sec}$  and  $C(x, t)$  is the chloride concentration at any position  $x$  at time  $t$ . In a real structure, if  $C(x, t)$  is assumed to be the chloride corrosion threshold and  $x$  is the thickness of concrete cover, then the corrosion initiation period,  $T_i$ , can be calculated based on a knowledge of the parameters  $C_0$  and  $D_c$ . For bridge decks under de-icing conditions  $C_0 = 1.6$ , as % of cement weight, is often used.

The time  $T_i$  to initiation of reinforcement corrosion is

$$T_i = \frac{(d_1 - D_1 / 2)^2}{4D_c} \left( \operatorname{erf}^{-1} \left( \frac{C_{cr} - C_0}{C_i - C_0} \right) \right)^2 \quad (8)$$

where  $C_i$  is the initial chloride concentration,  $C_{cr}$  is the critical chloride concentration at which corrosion starts, and  $d_1 - D_1 / 2$  is the concrete cover. For plain concrete of moderate strength ( $f_{cu} \approx 30 \text{ N/mm}^2$ ) reported values of  $D_c$  are in the range between  $1 \cdot 10^{-8}$  and  $5 \cdot 10^{-8} \text{ cm}^2/\text{sec}$ .

When corrosion has started then the diameter  $D_i(t)$  of the reinforcement bars at time  $t$  is modelled by

$$D_i(t) = D_1 - C_{corr} i_{corr} t \quad (9)$$

where  $D_1$  is the initial diameter,  $C_{corr}$  is a corrosion coefficient, and  $i_{corr}$  is the rate of corrosion. The area of a reinforcement bar is then modelled using the following formulation



$$A(t) = \begin{cases} nD_i^2 \frac{\pi}{4} & \text{for } t \leq T_I \\ n(D(t))^2 \frac{\pi}{4} & \text{for } T_I \leq t \leq T_I + D_i / (0.0203 \cdot i_{\text{corr}}) \\ 0 & \text{for } t > T_I + D_i / (0.0203 \cdot i_{\text{corr}}) \end{cases} \quad (10)$$

$$T_I = \frac{x_d^2}{4D_C(\text{erf}^{-1}(\frac{C_{\text{cr}}(x_d, t) - C_0}{C_i - C_0}))^2}, \quad D(t) = D_i - 0.0203 \cdot (t - T_I) \cdot i_{\text{corr}}$$

$A(t)$  is the area of reinforcement bars [ $\text{mm}^2$ ] at the time  $t$  years,  $n$  is the number of reinforcement bars,  $D_i$  is the diameter of a single bar [ $\text{mm}^2$ ] and  $T_I$  is the corrosion initiation time in years. The value "0.0203" in the estimation of  $D(t)$  will vary depending on the circumstances.

The initiation time of corrosion is determined based on values of  $C_0, C_i, D_C, x_d, C_{\text{cr}}$ . After the deterioration is started the corrosion rate is modelled by the corrosion current  $i_{\text{corr}}$  only.

The model for  $A(t)$  (and the value of  $i_{\text{corr}}$  used) relates to an average deterioration of the reinforcement in the concrete. An important aspect of corrosion in addition to the average corrosion is the maximum penetration (pitting of reinforcement). Pitting of reinforcement may have more influence on the reliability than the average deterioration due to localised much higher weakening of the reinforcement. The ratio  $R$  between the maximum penetration  $PC_{\text{max}}$  and the average penetration  $PC_{\text{av}}$  has been estimated by a number of authors to be between 4-10, see e.g. [7]. Pitting corrosion is not included in this investigation.

The stochastic variables used in the deterioration modelling are: initial chloride concentration on surface, initial chloride concentration in concrete, diffusion coefficient for the concrete, cover to reinforcement, critical chloride concentration, and rate of corrosion.

#### 4. Example

This following example is used to illustrate the proposed methodology. The example is based on an existing UK bridge, but some limitations and simplifications are made. The bridge was built in 1975.




Figure 1. Bridge data.

The bridge was designed for 45 units HB load, see [8]. The bridge has a span of 9.755 m, the width is  $2 \times 13.71$  m, and the slab thickness is 550 mm (see figure 1).

Based on the corrosion data shown in table 1 the expected area of the reinforcement as a function of time can be calculated, see figure 2.




Figure 2. Reinforcement area  $A(t)$  as a function of time.

Reliability profiles for the two limit states discussed in section 2 are calculated on the basis of the stochastic modelling shown in tables 1 and 2.

Stochastic variables: Yield line limit state				
No	Type	Par. 1	Par. 2	Description
1	Normal	550.0	10.0	Thickness of slab [mm]
2	LogNormal	30.0	6.0	Cube strength of concrete [MPa]
3	Normal	23.6	0.4	Density of concrete [kN/m <sup>3</sup> ]
4	LogNormal	289.0	25.0	Yield strength: longitudinal reinforcement [MPa]
5	Normal	60.0	8.0	Cover on longitudinal reinforcement [mm]
6	LogNormal	289.0	25.0	Yield strength: transverse reinforcement [Mpa]
7	Normal	86.0	8.0	Cover on transverse reinforcement [mm]
8	Fixed	10053.0	-	Longitudinal reinforcement area (initial) [mm <sup>2</sup> ]
9	Fixed	565.0	-	Transverse reinforcement area (initial) [mm <sup>2</sup> ]
10	Gumbel	0.352	0.026	Static load factor [-]
11	Normal	1.27	0.20	Dynamic load factor [-]
12	Normal	1.08	0.072	Chloride concentration on surface [%]
13	Fixed	0.0	-	Initial chloride concentration [%]
14	Normal	35.0	2.5	Diffusion Coefficient [cm <sup>2</sup> /sec]
15	Normal	0.4	0.05	Critical Chloride concentration [%]
16	Uniform	2.5	0.29	Corrosion parameter [-]
17	Normal	1.0	0.05	Model uncertainty variable [-]

Table 1. Stochastic modelling used for the ULS.

Stochastic variables: Crack width limit state				
No	Type	Par. 1	Par. 2	Description
1	Normal	60.0	9.0	Concrete cover [mm]
2	Normal	125.0	12.5	Distance between reinforcement bars [mm]
3	Normal	40.0	1.2	Diameter of reinforcement bar [mm]
4	Normal	550.0	27.0	Thickness of slab [mm]
5	Normal	200.0E3	6.0E3	Young's modulus [N/mm <sup>2</sup> ]
6	Normal	3.4	0.68	Tensile strength [N/mm <sup>2</sup> ]
7	Gumbel	1.0	0.10	Model uncertainty [-]
8	Gumbel	0.352	0.026	Static load factor [-]
9	Normal	1.27	0.20	Dynamic load factor [-]
10	Normal	1.08	0.072	Chloride concentration on surface [%]
11	Fixed	0.0	-	Initial chloride concentration [%]
12	Normal	35.0	2.5	Diffusion Coefficient [cm <sup>2</sup> /sec]
13	Normal	0.4	0.05	Critical Chloride concentration [%]
14	Uniform	2.5	0.29	Corrosion parameters [-]

Table 2. Stochastic modelling used for the SLS.

The general traffic highway load model in the Eurocode 1, Part 3 (ENV 1991-3:1995) for lane and axle load is applied. The load effects produced by the Eurocode model (lane and axle load) are multiplied by a static load factor (extreme type 1) and a dynamic load factor (normal). See e.g. stochastic variables 10 and 11 used for the yield line limit state. Several load cases are considered in the project. In this paper only the load case with 2 marked lanes loaded is included.

The normalised reliability profile for the yield line ULS (full width failure) and the corresponding probability of failure profile are shown in figure 3. The reliability index at time  $t=0$  is  $\beta_0=11.5$ . Due to the size of the concrete cover (mean value 60 mm) the deterioration does not have any effect until year 70.




Figure 3 : Reliability profiles using a yield line limit state.

The results from the sensitivity analysis with regard to the mean values are shown for  $t=0$  years and  $t=120$  years in figure 4. The most important variables are, as expected, the thickness of the slab, the yield strength of the reinforcement, and the model uncertainty. Observe that the magnitude of sensitivity with regard to the cover changes from negative at time  $t=0$  to positive at time  $t=120$  due to the corrosion.




Figure 4 : Sensitivity analysis for yield line limit state at  $t = 0$  years and at  $t = 120$  years.



The normalised reliability profile for the crack SLS and the corresponding probability of failure profile are shown in figure 5. The reliability index at time  $t=0$  is  $\beta_0=7.1$ . Due to the size of the concrete cover (mean value 60 mm) the deterioration does not have any effect until year 90.




Figure 5 : Reliability profiles using a crack width limit state

The results from the sensitivity analysis with regard to the mean values are shown for  $t=0$  years and  $t=120$  years in figure 6. The most important variables are as expected the concrete cover, the diameter of the reinforcement, the thickness of the slab, and Young's modulus. Observe that the magnitude of the sensitivity with regard to the cover is decreasing from time  $t=0$  to time  $t=120$  due to the corrosion.




Figure 6 : Sensitivity analysis for crack width limit state at  $t = 0$  years and at  $t = 120$  years.

## 5. Acknowledgement

The authors would like to thank the Highways Agency, London for permission to publish this paper. The work herein was carried out under a contract placed on CSRconsult by the HA. The authors are particularly grateful to Dr P. Das of the Highways Agency for his contributions to the fundamental philosophy of this work. However, any views expressed in this paper are not necessarily those of the Highways Agency of the U.K. Department of Transport.

## 6. References

- [1] Middleton, C. Example Collapse & Reliability Analyses of Concrete Bridges Using a new Analyses Technique. Cambridge University, 1994.
- [2] RELIAB01, Version 2.0 , manual and software. CSR-software, March 1994.
- [3] RELIAB02, Version 2.0 , manual and software. CSR-software, April 1994.
- [4] P. Thoft-Christensen: *"Reliability of Plastic Slabs"*, ICOSAR Conference, San Francisco, USA, August 1989.
- [5] CORROSION, Version 1.0 , manual and software. CSR-software, September 1995.
- [6] Eurocode 2: Design of concrete structures - Part 1-1: General rules and rules for buildings, ENV 1992-1:1991.
- [7] J .A. González, C. Andrade, C. Alonso & S. Feliu: *"Comparison of Rates of General Corrosion and Maximum Pitting Penetration on Concrete Embedded Steel Reinforcement"*, Cement and Concrete Research, Vol. 25, No. 2, pp. 257-264, 1995.
- [8] Department of Transport. Loads for Highway Bridges. Departmental Standard BD37/88, London, 1989.





## STRUCTURAL RELIABILITY THEORY SERIES

PAPER NO. 126: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Reliability Approximations for MDOF Structures with Random Properties subject to Random Dynamic Excitation in Modal Subspaces*. ISSN 0902-7513 R9440.

PAPER NO. 127: H. U. Köylüoğlu, S. R. K. Nielsen and A. Ş. Çakmak: *A Faster Simulation Method for the Stochastic Response of Hysteretic Structures subject to Earthquakes*. ISSN 0902-7513 R9523.

PAPER NO. 128: H. U. Köylüoğlu, S. R. K. Nielsen, A. Ş. Çakmak & P. H. Kirkegaard: *Prediction of Global and Localized Damage and Future Reliability for RC Structures subject to Earthquakes*. ISSN 0901-7513 R9426.

PAPER NO. 129: C. Pedersen & P. Thoft-Christensen: *Interactive Structural Optimization with Quasi-Newton Algorithms*. ISSN 0902-7513 R9436.

PAPER NO. 130: I. Enevoldsen & J. D. Sørensen: *Decomposition Techniques and Effective Algorithms in Reliability-Based Optimization*. ISSN 0902-7513 R9412.

PAPER NO. 131: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Approximate Forward Difference Equations for the Lower Order Non-Stationary Statistics of Geometrically Non-Linear Systems subject to Random Excitation*. ISSN 0902-7513 R9422.

PAPER NO. 132: I. B. Kroon: *Decision Theory applied to Structural Engineering Problems*. Ph.D.-Thesis. ISSN 0902-7513 R9421.

PAPER 133: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Stochastic Dynamics of Nonlinear Structures with Random Properties subject to Random Stationary Excitation*. ISSN 0902-7513 R9520.

PAPER NO. 134: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Solution of Random Structural System subject to Non-Stationary Excitation: Transforming the Equation with Random Coefficients to One with Deterministic Coefficients and Random Initial Conditions*. ISSN 0902-7513 R9429.

PAPER NO. 135: S. Englund, J. D. Sørensen & S. Krenk: *Estimation of the Time to Initiation of Corrosion in Existing Uncracked Concrete Structures*. ISSN 0902-7513 R9438.

PAPER NO. 136: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Solution Methods for Structures with Random Properties subject to Random Excitation*. ISSN 0902-7513 R9444.

PAPER NO. 137: J. D. Sørensen, M. H. Faber & I. B. Kroon: *Optimal Reliability-Based Planning of Experiments for POD Curves*. ISSN 0902-7513 R9455.

PAPER NO. 138: S.R.K. Nielsen & P.S. Skjærbæk, H.U. Köylüoğlu & A.Ş. Çakmak: *Prediction of Global Damage and Reliability based upon Sequential Identification and Updating of RC Structures subject to Earthquakes*. ISSN 0902-7513 R9505.

PAPER NO. 139: R. Iwankiewicz, S. R. K. Nielsen & P. S. Skjærbæk: *Sensitivity of Reliability Estimates in Partially Damaged RC Structures subject to Earthquakes, using Reduced Hysteretic Models*. ISSN 0902-7513 R9507.



## STRUCTURAL RELIABILITY THEORY SERIES

PAPER NO 141: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Uncertain Buckling Load and Reliability of Columns with Uncertain Properties*. ISSN 0902-7513 R9524.

PAPER NO. 142: S. R. K. Nielsen & R. Iwankiewicz: *Response of Non-Linear Systems to Renewal Impulses by Path Integration*. ISSN 0902-7513 R9512.

PAPER NO. 145: H. U. Köylüoğlu, S. R. K. Nielsen, Jamison Abbott and A. Ş. Çakmak: *Local and Modal Damage Indicators for Reinforced Concrete Shear Frames subject to Earthquakes*. ISSN 0902-7513 R9521

PAPER NO. 146: P. H. Kirkegaard, S. R. K. Nielsen, R. C. Micaletti and A. Ş. Çakmak: *Identification of a Maximum Softening Damage Indicator of RC-Structures using Time-Frequency Techniques*. ISSN 0902-7513 R9522.

PAPER NO. 147: R. C. Micaletti, A. Ş. Çakmak, S. R. K. Nielsen & P. H. Kirkegaard: *Construction of Time-Dependent Spectra using Wavelet Analysis for Determination of Global Damage*. ISSN 0902-7513 R9517.

PAPER NO. 148: H. U. Köylüoğlu, S. R. K. Nielsen & A. Ş. Çakmak: *Hysteretic MDOF Model to Quantify Damage for TC Shear Frames subject to Earthquakes*. ISSN 1395-7953 R9601.

PAPER NO. 149: P. S. Skjærbæk, S. R. K. Nielsen & A. Ş. Çakmak: *Damage Location of Severely Damaged RC-Structures based on Measured Eigenperiods from a Single Response*. ISSN 0902-7513 R9518.

PAPER NO. 150: S. R. K. Nielsen & H. U. Köylüoğlu: *Path Integration applied to Structural Systems with Uncertain Properties*. ISSN 1395-7953 R9602.

PAPER NO. 151: H. U. Köylüoğlu & S. R. K. Nielsen: *System Dynamics and Modified Cumulant Neglect Closure Schemes*. ISSN 1395-7953 R9603.

PAPER NO. 154: J. D. Sørensen, M. H. Faber, I. B. Kroon: *Optimal Reliability-Based Planning of Experiments for POD Curves*. ISSN 1395-7953 R9542.

PAPER NO. 155: J. D. Sørensen, S. Engelund: *Stochastic Finite Elements in Reliability-Based Structural Optimization*. ISSN 1395-7953 R9543.

PAPER NO. 156: C. Pedersen, P. Thoft-Christensen: *Guidelines for Interactive Reliability-Based Structural Optimization using Quasi-Newton Algorithms*. ISSN 1395-7953 R9615.

PAPER NO. 157: P. Thoft-Christensen, F. M. Jensen, C. R. Middleton, A. Blackmore: *Assessment of the Reliability of Concrete Slab Bridges*. ISSN 1395-7953 R9616.

PAPER NO. 161: S. Engelund, J. D. Sørensen: *Stochastic Models for Chloride-initiated Corrosion in Reinforced Concrete*. ISSN 1395-7953 R9608.

Department of Building Technology and Structural Engineering  
Aalborg University, Sohngaardsholmsvej 57, DK 9000 Aalborg  
Telephone: +45 98 15 85 22    Telefax: +45 98 14 82 43