



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Estimation of critical cooling rates for nucleation in phosphosilicate glasses

Liu, S.J.; Tao, H.Z.; Zhang, Y.F.; Yue, Yuanzheng

Published in:
The 24th International Congress on Glass - Abstracts

Creative Commons License
Unspecified

Publication date:
2016

Document Version
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):
Liu, S. J., Tao, H. Z., Zhang, Y. F., & Yue, Y. (2016). Estimation of critical cooling rates for nucleation in phosphosilicate glasses. In *The 24th International Congress on Glass - Abstracts* (pp. 266). International Commission on Glass (ICG).

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Estimation of critical cooling rates for nucleation in phosphosilicate glasses

Shujiang Liu^{1,2}, Haizheng Tao¹, Yanfei Zhang^{1,2}, Yuanzheng Yue^{1,2,3*}

¹State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan, Hubei 430070, China


²Key Laboratory of Processing and Testing Technology of Glass & Functional Ceramics of Shandong Province, Qilu University of Technology, Jinan 250353, China

³Department of Chemistry and Bioscience, Aalborg University, Aalborg DK-9000, Denmark

lsj-24@163.com

Crystallization of a liquid below the liquidus temperature is a complex process involving simultaneous nucleation and growth of crystallites.¹⁾ Nucleation is the crucial step of the whole crystallization process in liquid and determines the glass-forming ability. In most cases there exists a large temperature overlap between nucleation and crystal growth. It is known that The typical “TTT” diagram is used to measure critical cooling rate q_c^* of glass-forming liquids, and this is very time consuming and experimentally challenging. The determined q_c^* depends on the accuracy of determination of crystallinity and the resolution limit of the microscopic analyses. In this paper we attempt to derive a physical correlation between the cooling rate and nucleation, and to further obtain the q_c^* for glass formation from a liquid. We determine the critical cooling rates of some phosphosilicate liquids based on the differential scanning calorimetric (DSC) and viscometric measurements. The relation between the nucleation onset temperature and relatively low cooling rate can be obtained from DSC curves (Fig. 1). However, for the fast quenching process with larger cooling rate, the dependence of nucleation onset temperature on cooling rate is described by comparing both functions, $f_1(T)$ and $f_2(T)$, which are derived from the classical nucleation theory (Fig. 2).²⁾ $f_1(T)$ is cooling rate dependent, whereas $f_2(T)$ is independent on cooling rate. The crossover temperature above T_g for both curves corresponds to the nucleation onset temperature. Thus the q_c^* value is calculated at a crossover point between both $f_1(T)$ and $f_2(T)$ functions. The XRD results confirm the correlation between q_c and nucleation onset temperature of slow- and fast-quenched samples. The q_c of the fast quenched sample is determined from the relation between the cooling rate and the viscosity at fictive temperature.³⁾

(a)



(b)




Figure 1. C_p curves of the glasses underwent various cooling rates.

Figure 2. Two temperature functions derived from classical nucleation theory. Inset: nucleation onset temperatures with relatively low cooling rate.

1) H. Yinnon, D. R. Uhlmann, Applications of thermoanalytical techniques to the study of crystallization kinetics in glass-forming liquids, Part I: Theory, J. Non-Cryst. Solids, 54, (1983) 253-275.

2) D. Becker, W. Döring. The kinetic treatment of nuclear formation in supersaturated vapors, Annalen der Physik, 24 (1935), 719-752.

3) Y. Z. Yue, R. von der Ohe, S. L. Jensen, Fictive temperature, cooling rate, and viscosity of glasses, J. Chem. Phys., 120 (2004), 8053-8059.