

Aalborg Universitet

Fracture Toughness of a Metal-Organic Framework Glass
To, Theany; Sørensen, Søren Strandskov; Stepniewska, Malwina; Qiao, Ang; Jensen, Lars Rosgaard; Bauchy, Mathieu; Yue, Yuanzheng; Smedskjær, Morten Mattrup
Publication date: 2021
Link to publication from Aalborg University
Citation for published version (APA): To, T., Sørensen, S. S., Stepniewska, M., Qiao, A., Jensen, L. R., Bauchy, M., Yue, Y., & Smedskjær, M. M. (2021). Fracture Toughness of a Metal-Organic Framework Glass. Abstract from Engineering Mechanics

Institute Conference 2021.

General rightsCopyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
 You may not further distribute the material or use it for any profit-making activity or commercial gain
 You may freely distribute the URL identifying the publication in the public portal -

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Fracture Toughness of a Metal-Organic Framework Glass

Theany To¹, Søren S. Sørensen¹, Malwina Stepniewska¹, Ang Qiao¹, Lars R. Jensen², Matiheu Bauchy³, Yuanzheng Yue¹, Morten M. Smedskjaer¹

Metal-organic framework (MOF) glasses feature unique thermal, structural, and chemical properties compared to traditional metallic, organic, and oxide glasses. In practical engineering, the knowledge of their strength and toughness are important, yet the small sizes of MOF glasses limits the testing. Recently, the discovery of a zeolitic imidazolate framework (ZIF) glass with ultra-high glass forming ability, namely ZIF-62, has enabled the preparation of >25 mm³ samples and thus mechanical testing besides indentation. In this work, we report the first measurement of the fracture toughness ($K_{\rm Ic}$) of a bulk MOF material using a self-consistent single-edge precracked beam method and find it to be ~0.1 MPa m^{0.5}, which is low even compared to brittle oxide glasses and in between the values of foam and elastomers. Molecular dynamics simulations and theoretical calculations confirm the low $K_{\rm Ic}$ value of ZIF-62 glass, ascribing the origin to the weak coordinative bonds (Zn-N), which preferentially break during crack propagation.

¹ Department of Chemistry and Bioscience, Aalborg University, Aalborg, Denmark

² Department of Materials and Production, Aalborg University, Aalborg, Denmark

³ Department of Civil and Environmental Engineering, University of California, Los Angeles, USA